

ABSTRACT OF THE DISCLOSURE

502330

SA

5 Microtextured elastomeric laminates comprising  
at least one elastomeric layer and at least one thin skin  
layer is preferably prepared by coextrusion of the layers  
followed by stretching the laminate past the elastic limit  
of the skin layers in predetermined regions of the  
laminate and then allowing the laminate to recover in  
10 these regions.

EA

15

20

25

30

35

1